


## TECHNICAL DATA SHEET

## TK HQ GLOSS

TK HQ GLOSS is a gloss bioriented polypropylene film one side corona treated and the other side coated with adhesive, which is specifically designed for thermal lamination.

*This film is suitable to come into contact with food and complies with EN-71 (declarations on request).*



### TYPICAL TECHNICAL FEATURES <sup>(1)</sup>

PHYSICAL PROPERTIES		METHOD	UNIT	VALUE code 700/02
Thickness		Internal	µm	33
Grammage		Internal	g/m <sup>2</sup>	29,6
Surface tension	corona side	ASTM D2578	dyne/cm	≥ 38

THERMAL PROPERTIES		METHOD	UNIT	VALUE code 700/02
Lamination temperature	adhesive side	ASTM D1204	°C	100 - 120 <sup>(*)</sup>

<sup>(\*)</sup> variable according to the processing conditions. Best adhesion performance is usually 24h after laminating.

OPTICAL PROPERTIES		METHOD	UNIT	VALUE code 700/02
Gloss	45°	ASTM D2457	GU	≥ 58
	60°			≥ 95

### STORAGE

Store the material in a dry location (preferably with RH < 50%) at a constant temperature between 10°C and 30°C. Do not leave it exposed to direct sunlight or atmospheric agents. Partially used reels have to be repacked as originally supplied.

### WARRANTY

Material processability is guaranteed up to 6 months since shipment date, as long as it is stored correctly.

**<sup>(1)</sup> The information and data contained herein are to be used only as a guideline; therefore, ULTRALEN FILM GmbH doesn't offer any guarantee on their absolute truthfulness and doesn't accept any liability arising out of their use.**

#### ULTRALEN FILM GmbH

LUSTGARTENSTRASSE, 6 - 79576 WEIL AM RHEIN - DEUTSCHLAND  
USt.ID: DE229822516



It is recommended to condition the material at room temperature at least 24 hours before its use.

**DISCLAIMERS**

ULTRALEN FILM GmbH gives no warranty, expressed or implied, as to the suitability of the material for a specific application or characteristic use. An industrial homologation test of the material in actual conditions of purpose is always needed in order to verify its suitability for the specific application or characteristic use.

Before using the material, it is advisable to check the compatibility of the inks and adhesives to be purposed with the type and level of its treatment.

---

**ULTRALEN FILM GmbH**

LUSTGARTENSTRASSE, 6 - 79576 WEIL AM RHEIN - DEUTSCHLAND

USt.ID: DE229822516

Tel.: (0049) 76214223880 Fax: (0049) 76214223839

e-mail: [info@ultralen.com](mailto:info@ultralen.com) web: [www.ultralen.com](http://www.ultralen.com)